



# Technical

# Specifications

## I-40A

PARAMETERS	METHOD	GUARANTEED	ACTUAL
Kinematic viscosity @ 40 C, mm <sup>2</sup> /c	GOST 33	25-35	27,61
Acid value, mg KOH/1 g oil	GOST11362	0,03	0,02
Ash content, %	GOST1461	0,005	0,004
Mass fraction of sulphur, %	GOST51947	1,3	1,18
Sediment content	GOST6370	none	none
Water content	GOST2477	traces	traces
Density @ 20 C, kg/m <sup>3</sup>	GOST3900	890	882,8
Pour point, C	GOST20287	-15	-15
Color	GOST433	3,0	3,0
Flash point in an open cup, C	GOST18136	180	201
Oxidating stability: acidification, mg KOH/1 g of oil	GOST 18136 with an addition 5.2 TU 0253043-48120848-2005	0,30	0,10
Oxidating stability: resin growth, %	GOST 15886 with an addition 5.3 TU 0253043-48120848-2005	3,0	1,54
Solvent content in selective cleaning oils	GOST P 52532	none	none
Auto-ignition temperature, C	GOST 12.1.044	-	343

### Handling Health & Safety :

Lubricants consisting of highly refined mineral oils with specification additives. In normal conditions of use, this lubricant presents no particular toxic hazard. All lubricants, of any kind should be handled with great care, particularly avoiding can contact with the skin.

Prevent any splashing, and keep away from combustible materials. Store under cover and away from any risk of pollution. Dispose off the used oil correctly; don't pour down drains, into watercourses or the soil.

İNOVATİF MAKİNA PETROL LOJİSTİK İTHALAT  
İHRACAT SANAYİ VE TİCARET LİMİTED ŞİRKETİ  
KÜME EVLERİ TRAK DEPOLARI NO : 444 İÇ KAP / NO 6 MERKEZ / EDİRNE  
V.D : KIRKPINAR VKN : 663 094 0035



ASTM INTERNATIONAL